

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 01-103604

(43)Date of publication of application : 20.04.1989

---

(51)Int.Cl.

C08F 8/04  
C08F212/14

---

(21)Application number : 63-137091

(71)Applicant : MARUZEN PETROCHEM CO LTD

(22)Date of filing : 03.06.1988

(72)Inventor : OZAWA KAZUO  
MATSUMOTO OSAMU  
TAKAHASHI EIJI  
KUDO KAZUSHI  
AKAHO MITSURU  
OKADO HIDEO

---

(30)Priority

Priority number : 62178432 Priority date : 17.07.1987 Priority country : JP

---

### (54) IMPROVEMENT OF PROPERTY OF P-VINYLPHENOLIC POLYMER

(57)Abstract:

**PURPOSE:** To improve economically the properties of p-vinylphenolic polymer, such as permeability to light in the ultraviolet region, solubility, and thermal cracking resistance, by bringing a p-vinylphenolic polymer into contact with hydrogen in the presence of a catalyst of a Group VIII metal of the periodic table at a prescribed temperature.

**CONSTITUTION:** A p-vinylphenolic polymer is prepared which is, for example, a poly-p-vinylphenol obtained from crude p-vinylphenol as raw material or a copolymer obtained from p-vinylphenol and other comonomer. The p-vinylphenolic polymer is brought into contact with hydrogen in the presence of a catalyst of a Group VIII metal of the periodic table (e.g., a platinum catalyst or a nickel catalyst) and, preferably, in the presence of a solvent selected from the group consisting of lower alcohols, lower ketones, cyclic ethers and phenols (e.g., methanol) at 50W/300°C. Thus the properties of the p-vinylphenolic polymer can be easily improved.